

Casapark 209

Technical data

Type of wood	Oak
Grading	15
Colour	Creta
Surface structure	beveled 2V, brushed
Surface treatment	natural oiled
Format	2200 x 209 x 14 mm
Number of layers	3
Top layer thickness	~ 3.5 mm
Laying method	glued to subfloor
Connection	Tongue + groove
Packing unit	2.76 m ² /package
Wood origin	Oak: Europe, Spruce: Europe, Spruce: Europe
Label health and sustainability	
Wood label	Wood from controlled sources
eco-bau	«base», does not infringe criteria of exclusion of Minergie-ECO
Sentinel Haus institute	fulfilled
Cradle to Cradle Certified®	
Label on VOC-emissions for France	A
Release of formaldehyde according to EN 717-1	E 1
Density - top layer	~ 650 kg/m ³
Grammage	~ 8.08 kg/m ²
Hardness Brinell - top layer *1	~ 38 N/mm ²
Shrinkage and swelling *2	0.25 %
Floor heating (Thermal resistance)	very convenient (~0.109 m ² K/W)
Moisture content	5-9 %
Fire Resistance acc. to EN 14342 and EN 13501-1	Dfl-s1
Slip resistance grade	
according to bfu-regulations R-9729 *3	GS 3
according to CEN/TS 15676 *4	USRV 33
according to DIN-EN 51130 *5	R9
Product standard	

*1 at moisture content of 7 %

*2 top layer at free storage, based on a humidity change of 1 %

*3 Mechanical strength (shoe zone)

*4 Pendulum test

*5 inclined plane

Date: 03.06.24