

Cleverpark

Technical data

Type of wood	Cherry am.
Grading	14
Colour	
Surface structure	
Surface treatment	matt lacquered
Format	1250 x 100 x 9.5 mm
Number of layers	2
Top layer thickness	≥ 2.5 mm
Laying method	glued to subfloor
Packing unit	2 m ² /package
Wood origin	Cherry am.: North America, HDF: Germany
Label health and sustainability	
Wood label	Wood from controlled sources
eco-bau	
Sentinel Haus institute	fulfilled
Cradle to Cradle Certified TM	Bronze
Label on VOC-emissions for France	A+
Release of formaldehyde according to EN 717-1	E 1
Density - top layer	~ 610 kg/m ³
Grammage	~ 7.93 kg/m ²
Hardness Brinell - top layer *1	~ 29 N/mm ²
Shrinkage and swelling *2	0.25 %
Floor heating (Thermal resistance)	100% convenient (~0.05 m ² K/W)
Moisture content	5-9 %
Fire Resistance acc. to EN 14342 and EN 13501-1	Cfl-s1
Slip resistance grade	
according to CEN/TS 15676 *3	USRV 44
according to DIN-EN 51130 *4	R10
according to ÖNORM Z 1261 *5	Class 1
Product standard	EN 13489

*1 at moisture content of 7 %

Date: 06.05.21

*2 top layer at free storage, based on a humidity change of 1 %

*3 Pendulum test

*4 inclined plane

*5 Coefficient of friction