

Monopark

Technical data

Type of wood	Maple can.
Grading	15
Colour	
Surface structure	unbrushed
Surface treatment	matt lacquered
Format	470 x 70 x 9.6 mm
Number of layers	2
Top layer thickness	~ 3 mm
Laying method	glued to subfloor
Connection	Tongue + groove
Packing unit	2.11 m ² /package
Wood origin	Maple can.: Canada, HDF: Germany
Label health and sustainability	
Wood label	Wood from controlled sources
eco-bau	
Sentinel Haus institute	fulfilled
Cradle to Cradle Certified®	
Label on VOC-emissions for France	A+
Release of formaldehyde according to EN 717-1	E 1
Density - top layer	~ 680 kg/m ³
Grammage	~ 8.14 kg/m ²
Hardness Brinell - top layer *1	~ 40 N/mm ²
Shrinkage and swelling *2	0.28 %
Floor heating (Thermal resistance)	100% convenient (~0.05 m ² K/W)
Moisture content	5-9 %
Fire Resistance acc. to EN 14342 and EN 13501-1	Cfl-s1
Slip resistance grade	
according to bfu-regulations R-9729 *3	GS 3
according to CEN/TS 15676 *4	USRV 44
according to DIN-EN 51130 *5	R10
according to ÖNORM Z 1261 *6	Class 1
Product standard	EN 13489

*1 at moisture content of 7 %

*2 top layer at free storage, based on a humidity change of 1 %

*3 Mechanical strength (shoe zone)

*4 Pendulum test

*5 inclined plane

*6 Coefficient of friction

Date: 26.04.24