

Villapark

Technical data

Type of wood	Ash
Grading	13
Colour	Farina
Surface structure	beveled 2V, brushed
Surface treatment	B-Protect
Format	2100 x 190 x 9.5 mm
Number of layers	2
Top layer thickness	≥ 2.5 mm
Laying method	glued to subfloor
Packing unit	2.4 m ² /package
Wood origin	Ash: Europe, HDF: Germany
Label health and sustainability	
Wood label	Wood from controlled sources
eco-bau	«base», does not infringe criteria of exclusion of Minergie-ECO
Sentinel Haus institute	fulfilled
Cradle to Cradle Certified TM	Bronze
Label on VOC-emissions for France	A+
Release of formaldehyde according to EN 717-1	E 1
Density - top layer	~ 630 kg/m ³
Grammage	~ 8.32 kg/m ²
Hardness Brinell - top layer *1	~ 36 N/mm ²
Shrinkage and swelling *2	0.22 %
Floor heating (Thermal resistance)	100% convenient (~0.05 m ² K/W)
Moisture content	5-9 %
Fire Resistance acc. to EN 14342 and EN 13501-1	Cfl-s1
Slip resistance grade	
according to CEN/TS 15676 *3	USRV 94
according to DIN-EN 51130 *4	R10
according to ÖNORM Z 1261 *5	Class 1
Product standard	EN 13489

*1 at moisture content of 7 %

Date: 17.04.21

*2 top layer at free storage, based on a humidity change of 1 %

*3 Pendulum test

*4 inclined plane

*5 Coefficient of friction